

U-Lite™ – 4mm Danpalon Performance Summary

RV 01-12

Test Description	Test Procedure	Results & Comments
1) FLAMMABILITY Self-Ignition Smoke Density Burn Extent Interior Flame Spread	ASTM 1929-3 ASTM D2843 ASTM D635 ASTM E-84	1120° F 54% CC1 Rating Class A
2) WEATHERING Weathering Evaluation Color Change Yellowing Index Light Transmission	ASTM D4364-84 ASTM D2244 ASTM D1925 ASTM D1003	Successful exposure to concentrated natural sunlight radiation of 56000 MJ/M ² No more than 3.0 units Delta E after 60 mo. No more than 10 points after 60 mo. Shall not decrease more than 6% after 10 yrs.
3) IMPACT Hail resistance Large Missile Impact	ASTM E-222-81 SPI (Method B)	Panel repels hailstones of 25mm at velocity of 21 m/sec with no penetration 220 Ft. Lbs.

PANEL PROPERTIES AND DIMENSIONS

Standard Size: Glazing Panel = 23 5/8" (592 mm) wide x up to 19'5" long
 System Module = 23 3/4" wide (c/c with spacer) by up to 19'5" long

Weight of glazing panel: 0.98 LB / SF

Weight of entire panel system: 1.5 – 2 lbs / SF depending on system configuration

Thermal Expansion: Linear thermal expansion = 0.0000375 In/In/°F

U Value: Thermal insulation factor = 0.94 Btu/(hr)(ft²)(°F)

OPTICAL PROPERTIES

Color	STANDARD COLORS			CUSTOM COLORS			
	IW	White	Reflective	Green	Clear	Bronze	Blue
Visible Light Transmission	55%	40%	20%	75%	89%	38%	64%
Solar Transmission	58%	44%	18%	69%	80%	41%	73%
Solar Heat Gain Coefficient	0.61	0.48	0.28	0.72	0.81	0.50	0.75

LT - % of visible light transmission (400-700 nm)

ST- %of total solar radiation transmission (300-2800 nm)

SHGC – Solar Heat Gail Coefficient, total solar energy transmitted through the panel = %ST +0.2x[1-(%st+%sr)]

CPI DAYLIGHTING INC is engaged in continuing research to improve its products. Therefore, the right is reserved to modify or change the data provided in this Technical Summary without notice. This is descriptive literature and does not constitute warranties, expressed or implied. For statement of warranty, contact CPI.