

**VIRACON VS STAINLESS STEEL REFLECTIVE LAMINATED GLASS
(.060" PVB INTERLAYER) TABLE 3**

Product	Transmittance			Reflectance			U-Value		Shading Coefficient	Relative Heat Gain	SHGC	LSG	European U-Value
	Visible	Solar	U-V	Exterior	Interior	Solar	Winter	Summer					
VS 1-20	19%	12%	<1%	24%	31%	21%	.95	.87	.39	90	.33	0.58	5.3
VS 1-14	13%	8%	<1%	32%	36%	27%	.95	.87	.34	80	.29	0.45	5.3
VS 1-08	8%	5%	<1%	42%	36%	33%	.95	.87	.29	70	.24	0.33	5.3
VS 2-20	16%	8%	<1%	18%	31%	11%	.95	.87	.40	92	.34	0.47	5.3
VS 2-14	11%	5%	<1%	24%	36%	13%	.95	.87	.37	86	.31	0.35	5.3
VS 2-08	7%	3%	<1%	31%	36%	16%	.95	.87	.34	81	.29	0.24	5.3
VS 3-20	10%	7%	<1%	9%	31%	9%	.95	.87	.40	91	.34	0.29	5.3
VS 3-14	7%	5%	<1%	11%	36%	11%	.95	.87	.37	87	.32	0.22	5.3
VS 3-08	4%	3%	<1%	14%	36%	13%	.95	.87	.35	83	.30	0.13	5.3
VS 4-20	12%	8%	<1%	11%	31%	11%	.95	.87	.40	92	.34	0.35	5.3
VS 4-14	8%	5%	<1%	14%	36%	13%	.95	.87	.37	86	.31	0.26	5.3
VS 4-08	5%	3%	<1%	18%	36%	16%	.95	.87	.34	81	.29	0.17	5.3
VS 6-20	16%	8%	<1%	19%	31%	12%	.95	.87	.40	92	.34	0.47	5.3
VS 6-14	11%	6%	<1%	25%	36%	15%	.95	.87	.37	85	.31	0.35	5.3
VS 6-08	7%	4%	<1%	32%	36%	18%	.95	.87	.34	80	.29	0.24	5.3
VS 19-20	14%	9%	<1%	15%	31%	13%	.95	.87	.40	92	.34	0.41	5.3
VS 19-14	9%	6%	<1%	19%	36%	16%	.95	.87	.37	85	.31	0.29	5.3
VS 19-08	6%	4%	<1%	24%	36%	19%	.95	.87	.33	79	.28	0.21	5.3
VS 24-20	20%	16%	<1%	25%	33%	26%	.95	.87	.40	91	.34	0.59	5.3
VS 24-14	14%	11%	<1%	34%	38%	34%	.95	.87	.33	78	.28	0.50	5.3
VS 24-08	8%	7%	<1%	44%	37%	43%	.95	.87	.26	65	.22	0.36	5.3
VS 26-20	12%	7%	<1%	12%	31%	11%	.95	.87	.40	91	.34	0.35	5.3
VS 26-14	8%	5%	<1%	16%	36%	13%	.95	.87	.37	86	.31	0.26	5.3
VS 26-08	5%	3%	<1%	20%	36%	16%	.95	.87	.34	81	.29	0.17	5.3